



## Technical Information and Typical Properties

### HPB Supreme Blown Hand Film

**.57 mil**

---

#### Product Description

---

Supreme blown hand film is Sigma's "top of the line" blown hand film for the most difficult applications. Ideal for distribution centres that have difficult C-type pallets but is versatile enough to be used in most applications for enhanced load containment.

---

#### General

---

Applications      •Brick & Block•Warehouse•Irregular Loads•Transportation Industry•Food  
 Distribution•Bagged Products•Boxed Products•All Applications  
 Revision Date      6/22/2015      Available in widths from 11"-18"

Film Properties	Typical Value		Test Method
	(English)	Tolerance	
Tensile Strength at Yield MD	1600 psi	± 15%	ASTM D882
Tensile Strength at Yield TD	1700psi	± 15%	ASTM D882
Tensile Strength at Break MD	7000psi	± 15%	ASTM D882
Tensile Strength at Break TD	4900psi	± 15%	ASTM D882
Elongation at Break MD	450%	± 15%	ASTM D882
Elongation at Break TD	600%	± 15%	ASTM D882
Protrusion Puncture	7.1 lbs	± 15%	ASTM D5748
Protrusion Puncture Energy	14.3 in-lb	± 15%	ASTM D5748
Elmendorf Tear Strength MD	160 g/mil	± 15%	ASTM D1922
Elmendorf Tear Strength TD	750 g/mil	± 15%	ASTM D1922
Cling - Outside to Inside @ 225%	min 150 g/in	± 15%	ASTM D5458

---

Dimensions	Value	Tolerance
Core ID	3.05 inches	± 0.05 in
Film Thickness	14.5 micron	

---

Manufactured with pride in the USA and Canada by  
**Sigma Stretch Film**  
 Page & Schuyler Aves. Bldg #8  
 Phone: 800-672-9727 • 201-507-9100  
 Email: Sigma.Stretch@sigmaplastics.com  
 Visit our website at [www.sigmastretchfilm.com](http://www.sigmastretchfilm.com)  
 ©Copyright 2015 MSC Marketing & Technology, Inc.