



## Technical Information and Typical Properties

### LSC Extended Core Hand Film

#### 1.15 mil

---

#### Product Description

LSC is a premium cast bundling film available in 3" and 5" widths. It is ideal for unitizing several small items into one package or even for applying to the top of a pallet load of products to enhance stability, allowing an operator to safely move the pallet throughout the building.

---

#### General

Applications

•Distribution•Moving and Storage•Boxed Products•Transportation Industry•

Revision Date

6/22/2015

Available in widths from 3" & 5"

Film Properties	Typical Value		
	(English)	Tolerance	Test Method
Tensile Strength at Yield MD	1350 psi	± 15%	ASTM D882
Tensile Strength at Yield TD	1200psi	± 15%	ASTM D882
Tensile Strength at Break MD	8400psi	± 15%	ASTM D882
Tensile Strength at Break TD	4000psi	± 15%	ASTM D882
Elongation at Break MD	650%	± 15%	ASTM D882
Elongation at Break TD	900%	± 15%	ASTM D882
Protrusion Puncture	13.0 lbs	± 15%	ASTM D5748
Protrusion Puncture Energy	29.9 in-lb	± 15%	ASTM D5748
Elmendorf Tear Strength MD	300 g/mil	± 15%	ASTM D1922
Elmendorf Tear Strength TD	550 g/mil	± 15%	ASTM D1922
Cling - Outside to Inside @ 225%	min 150 g/in	± 15%	ASTM D5458

---

Dimensions	Value	Tolerance
Core ID	3.05 inches	± 0.05 in
Film Thickness	29.2 micron	

---

Manufactured with pride in the USA and Canada by

#### **Sigma Stretch Film**

Page & Schuyler Aves. Bldg #8

Phone: 800-672-9727 • 201-507-9100

Email: [stretch.info@sigmaplastics.com](mailto:stretch.info@sigmaplastics.com)

Visit our website at [www.sigmastretchfilm.com](http://www.sigmastretchfilm.com)

©Copyright 2018 Sigma Stretch Film