



Technical Information and Typical Properties

MPB Secure Blown Machine Film

.70 mil

Product Description

Sigma Secure Blown machine film combines extraordinary load-holding force with exceptional tear resistance to create a film which excels in containing heavy B and C loads. The films aggressive cling package promotes bonding between layers, eliminating tails.

General

Applications •Brick & Block•Warehouse•Irregular Loads•Transportation Industry•Food
 Distribution•Bagged Products•Boxed Products•All Applications
 Revision Date 6/22/2015 Available in widths from 20" & 30"

Film Properties	Typical Value		Test Method
	(English)	Tolerance	
Tensile Strength at Yield MD	1600 psi	± 15%	ASTM D882
Tensile Strength at Yield TD	1700psi	± 15%	ASTM D882
Tensile Strength at Break MD	7000psi	± 15%	ASTM D882
Tensile Strength at Break TD	4900psi	± 15%	ASTM D882
Elongation at Break MD	520%	± 15%	ASTM D882
Elongation at Break TD	730%	± 15%	ASTM D882
Protrusion Puncture	9.3 lbs	± 15%	ASTM D5748
Protrusion Puncture Energy	18.0 in-lb	± 15%	ASTM D5748
Elmendorf Tear Strength MD	160 g/mil	± 15%	ASTM D1922
Elmendorf Tear Strength TD	750 g/mil	± 15%	ASTM D1922
Cling - Outside to Inside @ 225%	min 150 g/in	± 15%	ASTM D5458

Dimensions	Value	Tolerance
Core ID	3.05 inches	± 0.05 in
Film Thickness	17.8 micron	

Manufactured with pride in the USA and Canada by

Sigma Stretch Film

Page & Schuyler Aves. Bldg #8

Phone: 800-672-9727 • 201-507-9100

Email: stretch.info@sigmaplastics.com

Visit our website at www.sigmastretchfilm.com

©Copyright 2018 Sigma Stretch Film