



Technical Information and Typical Properties

MSC Two-Sided Cling Machine Film 1.20 mil



Product Description

Sigma Select is our most versatile and cost effective cast machine film. Designed to be a workhorse, Sigma Select is a robust 2 sided cling film with a broad range of gauges that make it an ideal choice for most applications.

General

Applications: High Volume, Lower speed wrapping, One-sided cling not required
 Revision Date: 6/22/2015 Available in 20 and 30 inch widths

Film Properties	Typical Value (English)	Tolerance	Test Method
Tensile Strength at Yield MD	1300 psi	± 15%	ASTM D882
Tensile Strength at Yield TD	1200psi	± 15%	ASTM D882
Tensile Strength at Break MD	6900psi	± 15%	ASTM D882
Tensile Strength at Break TD	4000psi	± 15%	ASTM D882
Elongation at Break MD	540%	± 15%	ASTM D882
Elongation at Break TD	650%	± 15%	ASTM D882
Protrusion Puncture	12.2 lbs	± 15%	ASTM D5748
Protrusion Puncture Energy	34.6 in-lb	± 15%	ASTM D5748
Elmendorf Tear Strength MD	330 g/mil	± 15%	ASTM D1922
Elmendorf Tear Strength TD	530 g/mil	± 15%	ASTM D1922
Cling - Outside to Inside @ 225%	min 150 g/in	± 15%	ASTM D5458

Dimensions	Value	Tolerance
Core ID	3.05 inches	± 0.05 in
Film Thickness	30.5 micron	

Manufactured with pride in the USA and Canada by

Sigma Stretch Film

Page & Schuyler Aves. Bldg #8

Phone: 800-672-9727 • 201-507-9100

Email: stretch.info@sigmaplastics.com

Visit our website at www.sigmastretchfilm.com

©Copyright 2018 Sigma Stretch Film