



## Technical Information and Typical Properties

### MSC Two-Sided Cling Machine Film .70 mil




---

#### Product Description

---

Sigma Select is our most versatile and cost effective cast machine film. Designed to be a workhorse, Sigma Select is a robust 2 sided cling film with a broad range of gauges that make it an ideal choice for most applications.

---

#### General

---

Applications: High Volume, Lower speed wrapping, One-sided cling not required  
 Revision Date: 6/22/2015 Available in 20 and 30 inch widths

Film Properties	Typical Value (English)	Tolerance	Test Method
Tensile Strength at Yield MD	1250 psi	± 15%	ASTM D882
Tensile Strength at Yield TD	1200psi	± 15%	ASTM D882
Tensile Strength at Break MD	6900psi	± 15%	ASTM D882
Tensile Strength at Break TD	4000psi	± 15%	ASTM D882
Elongation at Break MD	430%	± 15%	ASTM D882
Elongation at Break TD	600%	± 15%	ASTM D882
Protrusion Puncture	9.5 lbs	± 15%	ASTM D5748
Protrusion Puncture Energy	21.0 in-lb	± 15%	ASTM D5748
Elmendorf Tear Strength MD	330 g/mil	± 15%	ASTM D1922
Elmendorf Tear Strength TD	530 g/mil	± 15%	ASTM D1922
Cling - Outside to Inside @ 225%	min 150 g/in	± 15%	ASTM D5458

---

Dimensions	Value	Tolerance
Core ID	3.05 inches	± 0.05 in
Film Thickness	17.8 micron	

---

Manufactured with pride in the USA and Canada by

### **Sigma Stretch Film**

Page & Schuyler Aves. Bldg #8

Phone: 800-672-9727 • 201-507-9100

Email: stretch.info@sigmaplastics.com

Visit our website at [www.sigmastretchfilm.com](http://www.sigmastretchfilm.com)

©Copyright 2018 Sigma Stretch Film