

Technical Information and Typical Properties

Sigma Stretch Film Vortex™ .80 mil One Sided Cling Blown Machine Film



Product Description

Sigma Vortex is a 3 layer blown film with one sided cling properties. Toughness, containment, and puncture resistance ensures problem free wrapping with clarity similar to most cast films.

General

Applications	• Bagged Product	• Ringer Applications	• Brick and Block
Revision Date	• High Containment	• Inboard Loads	• Bottled Water
	• 3/12/15		

Film Properties	Typical Value (English)	Tolerance	Typical Value (SI)	Tolerance	Test Method
Tensile Strength at Yield MD	2100	± 15%	13.8 mPa	--	ASTM D882
Tensile Strength at Yield TD	1400	± 15%	11.0 mPa	± 15%	ASTM D882
Tensile Strength at Break MD	5400 psi	± 15%	35.9 mPa	± 15%	ASTM D882
Tensile Strength at Break TD	4500 psi	± 15%	38.6 mPa	± 15%	ASTM D882
Elongation at Break MD	460%	± 15%	500%	± 15%	ASTM D882
Elongation at Break TD	580%	± 15%	600%	± 15%	ASTM D882
Protrusion Puncture	7.8 lbs	± 15%	5.7 kg	± 15%	ASTM D5748
Protrusion Puncture Energy	26.5 in-lb	± 15%	3.8 n-m	± 15%	ASTM D5748
Elmendorf Tear Strength MD	180 g/mil	± 15%	12.6 g/micron	± 15%	ASTM D1922
Elmendorf Tear Strength TD	1100 g/mil	± 15%	26.0 g/micron	± 15%	ASTM D1922
Cling - Outside to Inside @ 225%	min 150 g/in	± 15%	min 59 g/cm	± 15%	ASTM D5458

Dimensions	Value (English)	Tolerance	Value (SI)	Tolerance
Core ID	3.05 inches	± 0.05 in	76.2 mm	± 1.3 mm
Film Thickness	0.8 mil		20.3 micron	

Manufactured with pride in the USA by

Sigma Stretch Film

Page & Schuyler Aves. Bldg #8

Phone: 800-672-9727 • 201-507-9100

Email: stretch.info@sigmaplastics.com

Visit our website at www.sigmastretchfilm.com

©Copyright 2018 Sigma Stretch Film