



Technical Information and Typical Properties

MIT One Sided Cling Machine Film .75 mil



Product Description

Sigma Summit is Sigma's ultra-performance one-side cling, cast film. Summit sets the industry standard with this high quality, consistent machine film perfectly suited for high speed wrapper applications. Summit, in conjunction with our Rite-Gauging methodology will get more product to its destination in as-made condition.

General

Applications	High Volume	High speed wrapping	One-sided cling required
Revision Date	6/22/2015	Available in 20 and 30 inch widths	

Film Properties	Typical Value		Test Method
	(English)	Tolerance	
Tensile Strength at Yield MD	1350 psi	± 15%	ASTM D882
Tensile Strength at Yield TD	1250psi	± 15%	ASTM D882
Tensile Strength at Break MD	6700psi	± 15%	ASTM D882
Tensile Strength at Break TD	4000psi	± 15%	ASTM D882
Elongation at Break MD	500%	± 15%	ASTM D882
Elongation at Break TD	620%	± 15%	ASTM D882
Protrusion Puncture	11.8 lbs	± 15%	ASTM D5748
Protrusion Puncture Energy	23.0 in-lb	± 15%	ASTM D5748
Elmendorf Tear Strength MD	300 g/mil	± 15%	ASTM D1922
Elmendorf Tear Strength TD	600 g/mil	± 15%	ASTM D1922
Cling - Outside to Inside @ 225%	min 150 g/in	± 15%	ASTM D5458

Dimensions	Value	Tolerance
Core ID	3.05 inches	± 0.05 in
Film Thickness	19.0 micron	

Manufactured with pride in the USA and Canada by

Sigma Stretch Film

Page & Schuyler Aves. Bldg #8

Phone: 800-672-9727 • 201-507-9100

Email: stretch.info@sigmaplastics.com

Visit our website at www.sigmaplastics.com

©Copyright 2018 Sigma Stretch Film