



Sigma Stretch Film[®]

THE INDUSTRY LEADER

Technical Information and Typical Properties

MIT One Sided Cling Machine Film .57 mil



Product Description

Sigma Summit is Sigma's ultra-performance one-side cling, cast film. Summit sets the industry standard with this high quality, consistent machine film perfectly suited for high speed wrapper applications. Summit, in conjunction with our Rite-Gauging methodology will get more product to its destination in as-made condition.

General

Applications High Volume High speed wrapping One-sided cling required
Revision Date 6/22/2015 Available in 20 and 30 inch widths

| Film Properties | Typical Value | | Test Method |
|----------------------------------|---------------|-----------|-------------|
| | (English) | Tolerance | |
| Tensile Strength at Yield MD | 1350 psi | ± 15% | ASTM D882 |
| Tensile Strength at Yield TD | 1250psi | ± 15% | ASTM D882 |
| Tensile Strength at Break MD | 6700psi | ± 15% | ASTM D882 |
| Tensile Strength at Break TD | 4000psi | ± 15% | ASTM D882 |
| Elongation at Break MD | 480% | ± 15% | ASTM D882 |
| Elongation at Break TD | 600% | ± 15% | ASTM D882 |
| Protrusion Puncture | 10.3 lbs | ± 15% | ASTM D5748 |
| Protrusion Puncture Energy | 17.8 in-lb | ± 15% | ASTM D5748 |
| Elmendorf Tear Strength MD | 300 g/mil | ± 15% | ASTM D1922 |
| Elmendorf Tear Strength TD | 600 g/mil | ± 15% | ASTM D1922 |
| Cling - Outside to Inside @ 225% | min 150 g/in | ± 15% | ASTM D5458 |

| Dimensions | Value | Tolerance |
|----------------|-------------|-----------|
| Core ID | 3.05 inches | ± 0.05 in |
| Film Thickness | 14.5 micron | |

Manufactured with pride in the USA and Canada by

Sigma Stretch Film

Page & Schuyler Aves. Bldg #8

Phone: 800-672-9727 • 201-507-9100

Email: Sigma.Stretch@sigmaplastics.com

Visit our website at www.sigma.info@sigmaplastics.com

©Copyright 2018 Sigma Stretch Film