

## ENDURE BLOWN HAND FILM .80 mil

## **Product Description**

Composed of 25% of post-consumer recyclate (PCR) up to 50% other recycled materials, and 25% virgin materialsEndure's durability makes it versatile in any hand film application. Sigma Stretch Film has partnered with professional recyclers that have the capacity and capability to collect and convert used stretch film into PCR, supporting a circular production cycle. Available in widths from 11 inches to 18 inches.

## Applications

Toughness required Hand wrapping

SIGMA	
END	LRE

Film Properties	Typical Value (English)	Tolerance	Test Method
Tensile Strength at Yield MD	1600 psi	± 15%	ASTM D882
Tensile Strength at Yield TD	1700 psi	± 15%	ASTM D882
Tensile Strength at Break MD	6800 psi	± 15%	ASTM D882
Tensile Strength at Break TD	4600 psi	± 15%	ASTM D882
Elongation at Break MD	470%	± 15%	ASTM D882
Elongation at Break TD	720%	± 15%	ASTM D882
Protrusion Puncture	8.8 lbs.	± 15%	ASTM D5748
Protrusion Puncture Energy	15.0 in-lb	± 15%	ASTM D5748
Elmendorf Tear Strength MD	150 g/mil	± 15%	ASTM 1922
Elmendorf Tear Strength TD	500 g/mil	± 15%	ASTM 1922
Cling - Outside to Inside @ 225%	min 150 g/in	± 15%	ASTM D5458

Dimensions	Value	Tolerance
Core ID	3.05 inches	± 0.05%
Film Thickness	20.3 micron	

## Manufactured with pride in the USA and Canada by Sigma Stretch Film

Page & Schuyler Aves. Bldg #8 Phone: 800-672-9727 • 201-507-9100 Email: stretch.info@sigmaplastics.com Visit our website at www.sigmastretchfilm.com ©Copyright 2018 Sigma Stretch Film